

**SELF-ADHESIVE TACKY ADHESIVE AGENT AND TACKY ADHESIVE MATERIAL CONTAINING AGENT**

**Patent number:** JP2092982  
**Publication date:** 1990-04-03  
**Inventor:** YATSUKA NOBUAKI; MORIOKA AKIRA; MITSUNAGA SATORU  
**Applicant:** NITTO DENKO CORP  
**Classification:**  
- **International:** *B65B27/00; C09J7/02; C09J11/08; C09J153/02; B65B27/00; C09J7/02; C09J11/00; C09J153/00; (IPC1-7): B65B27/00; C09J7/02; C09J11/08; C09J153/02*  
- **European:**  
**Application number:** JP19880247178 19880930  
**Priority number(s):** JP19880247178 19880930

**Report a data error here**

**Abstract of JP2092982**

**PURPOSE:** To obtain the subject tacky adhesive agent having stronger adhesive force between the tacky adhesive faces than between the adhesive and an adherend and having excellent suitability for cutting with a cutter by compounding a specific compound to a block copolymer of a monovinyl-substituted aromatic compound and a conjugated diene compound. **CONSTITUTION:** The title tacky adhesive agent can be produced by compounding (A) 100 pts.wt. of a base polymer composed of a monovinyl-substituted aromatic compound and a conjugated diene compound and (B) preferably 5-50 pts.wt. of a chelate compound composed of an alkaline-earth metal. The component A is e.g., styrene-isoprene-styrene block copolymer and the component B is produced e.g., by reacting an alkaline-earth metal oxide such as calcium oxide to a resin containing functional group. The above functional group-containing resin is preferably an alkylphenolic resin.

---

Data supplied from the *esp@cenet* database - Worldwide